

Polyimide Laminate and Prepreg

Isola Laminate Systems offers a product line of polyimide-based prepreg and copper clad laminates for high temperature printed circuit applications. These products consist of a flame resistance, polyimide resin system suitable for military, commercial or industrial electronic applications requiring superior performance and the utmost in thermal properties. They utilize a polyimide and thermoplastic blend resin, fully cured without the use of MDA (Methylene Dianiline). This results in a polymer with a high Tg without the characteristic difficulties of brittleness and low initial bond strength associated with traditional thermoset polyimides.

Performance and Processing Advantages

- **High Tg - 260 °C (TMA)**
Greater thermal performance over epoxy-bismaleimide blends
- **Maintains Bond Strength at High Temperature**
- **Tough Resin System**
Improved processing due to less brittleness
Less delamination from machining
- **Flammability Rating V-0**
- **Non-MDA (Methylene Dianiline) Chemistry**
Meets all OSHA 1910.1050 requirements

Purchasing Information

- **Industry Approvals**
IPC-4101A /41
UL Recognized – GPY, File Number E41625
- **Standard Availability**
Thickness: 0.0025" [.05 mm] to 0.125" [3.2 mm]
Available in sheet or panel form
Copper Foil Cladding: Grade 3 (HTE), ½, 1 and 2 oz.
Foil Options: Double treat, Copper-Invar-Copper
Prepregs: Available in roll or panel form
Glass Styles: 106, 1080, 2313, 2116, and 7628

P96 Typical Laminate Properties, 0.008" [0.20mm]

PROPERTY	UNITS	IPC-4101A Spec /41	P96 Value	CONDITIONING
Thickness	inches mm	0.0197 [<0.50]	.008 [0.20]	— —
Glass Construction Retained Resin	— %	— —	2313/2116 47	— —
Thermal				
Tg (DSC)	°C	250 min.	260	E-2/105
CTE x-axis	ppm/°C	—	13	Ambient to Tg
y-axis	ppm/°C	—	17	Ambient to Tg
z-axis	ppm/°C	—	60	Ambient to 288°C
Thermal Stress, 10 s @, 288°C	seconds	pass visual	NA	Condition A
Thermal Stress, 10 s @, 288°C	seconds	—	>1100	E-2/105
Electrical				
Permittivity (DK) @				
1 MHz (2 Fluid Cell)	—	5.4 max.	4.6	C-24/23/50
500 MHz (HP4291)	—	—	4.0	C-24/23/50
1GHz (HP4291)	—	—	4.0	C-24/23/50
Loss Tangent (DF) @				
1 MHz (2 Fluid Cell)	—	0.035 max.	0.014	C-24/23/50
500 MHz (HP4291)	—	—	0.012	C-24/23/50
1 GHz (HP4291)	—	—	0.014	C-24/23/50
Volume Resistivity	megohms-cm	1x10 ⁴ min.	1.5x10 ⁹	C-96/35/90
	megohms-cm	6x10 ⁴ min.	2.3x10 ⁸	E-24/204
Surface Resistivity	megohms	1x10 ⁴ min.	3.0x10 ⁶	C-96/35/90
	megohms	6x10 ⁴ min.	2.1x10 ⁵	E-24/204
Electric Strength	volt/mil [volts/mm]	737 min. [2.90x10 ⁴]	1424 [5.6x10 ⁴]	D-48/50 D-48/50
Arc Resistance	seconds	120 min.	135	D-48/50
Comparative Tracking Index	volts PLC-UL	— —	<175 4	ASTM D-36/38-85 UL 746A
Physical				
Peel Strength, RTF ½ oz.	lb/in [Kg/M]	AABUS* AABUS	5.0 [90]	After Thermal Stress After Thermal Stress
Peel Strength, Std. 1 oz.	lb/in [Kg/M]	4.0 min. [70] min.	7.9 [141]	After Thermal Stress After Thermal Stress
	lb/in [Kg/M]	— —	6.4 [114]	E-1/170 E-1/170
Flammability	rating	HB	V-0	UL94
Moisture Absorption	%	1.0 max.	0.40**	D-24/23

* As agreed upon between user and supplier

** Material Thickness Tested 0.028"

ORDERING INFORMATION

USA
Isola Laminate Systems
7400 West Detroit Street, Suite 170
Chandler, Arizona 85226
Phone: 1-800-845-2904
Fax: 1-800-344-1825
E-mail: usa@isolaAG.com
www.isola-usa.com

Asia
Isola Pacific (Hong Kong) Ltd.
Unit 2508-18, Tower 1 Metroplaza
223 Hing Fong Road,
Kwai Chung, N.T.
Hong Kong
Phone: + 8 52 / 24 18-13 18
Fax: + 8 52 / 24 18-15 33
E-mail: asia@isolaAG.com
www.isolaAG.com

Europe
Isola AG
52348 Duren
Germany
Phone: + 49(0) 24 21 / 80 80
Fax: + 49 (0) 24 21 / 80 81 64
E-mail: europe@isolaAG.com
www.isolaAG.com

Pre-Conditioning Nomenclature

Letter	Meaning
A	No conditioning
C	Preconditioning in moist air
D	Preconditioning by immersion in H ₂ O
des	Preconditioning by drying over a desiccant
E	Preconditioning at temperature
R	Recovering 1~2 hours @ 15 - 35°C & 73 - 77% RH
T	Testing at a given temperature

Examples

C-96/40/92: 96 hours conditioning @ 40°C & 92% RH

D-24/23: 24 hours immersion in H₂O @ 23°C

E-1/100: temperature conditioning in 1 hour @ 100°C

E-1008/100: temperature conditioning 1008 hours @ 100°C

E-1/105 + des: temperature conditioning 1 hour @ 105°C drying over desiccant

D-24/23: immersion in H₂O @ 23°C for 24 hours

"The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold"